

SMX-15P

Revision: 16/07/2021

Page 1 from 2

Technical data

Basis	SMX Hybrid Polymer
Consistency	Paste
Curing system	Chemical curing
Density	1,84 g/ml
Temperature resistance**	-40 °C till +90 °C (cured)
Open time (23°C, 55% RV)*	Ca. 10 min.
Adjustable until	10 - 15 minutes
Shear strength**	> 3,00 N/mm ²
Can be loaded after*	min. 48h
Sandable/Paintable after	min. 48h
Resistance against aging	Good
Application temperature	15 °C → 25 °C
Consumption*	Approx. 10 meter/sausage

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

SMX-15P is a solvent, and water-free universal parquet adhesive. Suitable for bonding multilayer parquet on a structure of wooden beams.

Properties

- 1-component system ready for use
- Solvent free
- Contains no water
- Free of isocyanate
- Easy application
- Suitable for underfloor heating
- Very high final strength

Applications

- Engineered parquet with a maximum width of 200mm and a minimal thickness of 14mm.
- Bonding of multilayer parquet on a structure of wooden beams.

Packaging

Colour: light brown

Packaging: 600 ml foil bag

Shelf life

12 months in unopened packaging in a cool

and dry storage place at temperatures between +5°C and +25°C.

Substrates

Nature: SMX-15P should be applied on a rigid, clean, permanently dry, dust and grease free surface which do not contain any loose parts, paint, wax, oil or other contaminants.

Irregularities such as remaining concrete leveling, old adhesives may adversely affect adhesion. These need preferably to be removed mechanically for example by sanding or blasting. The top layer of anhydrite subfloors has to be removed.

Before installation of the parquet, the substrate should be checked to ensure it is suitable.

Check the moisture content throughout the entire thickness of the substrate with a carbide or electric hygrometer. Note that an electric hygrometer only gives indicative values. The moisture content must correspond the recommendation of the floor manufacturer (generally max. 2% for sand cement substrates and max. 0,5% for anhydrite, measured with a carbide hygrometer. For substrates with underfloorheating the values are resp. max. 1,5% and 0,3%). We recommend a preliminary adhesion test on any substrate.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

SMX-15P

Revision: 16/07/2021

Page 2 from 2

Parquet

The parquet flooring must be acclimatised for several days in the area where it is to be installed. Leave the parquet in its original packaging until installation to avoid any deformation. Check before installation that the moisture content of the wood is as recommended by the supplier, (generally 9% +/- 2%). If the humidity of the wood is more than 11% installation is not recommended. Allow a gap of 1 to 1,5 cm around the perimeter of the laid parquet, including any columns or structures, which penetrate the floor.

Application method

SMX-15P should be acclimatised to room temperature before installation. Apply the adhesive by means a caulking gun and V-cut nozzle on the subfloor. Do not apply more to the surface than can be covered with parquet within 30 minutes. Slide the parquet onto the adhesive layer and tap into place or tamp down with a rubber hammer. If necessary load the parquet with weight. Wait at least 24 hours before sanding and finishing the parquet. Cleaning: SMX-15P can be removed before curing from tools and material with Soudal Adhesive Cleaner 90A, Swipex or white spirit. Cured SMX-15P can only be removed mechanically.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

- Minimum temperature of the substrate should be at least 15°C.
- Do not apply the adhesive when the relative humidity is above 75%.
- Never install flooring on a substrate which contains too much moisture or on substrates with a higher humidity value than recommended by the wood supplier.

- Never install wood which is too dry (<7% humidity). It can expand at higher humidity and cause damage.
- Do not install if the walls and ceilings of the area are not dry (e.g. after plastering or painting etc.)
- Do not dilute the adhesive.
- Never apply on a substrate which is not protected against rising damp. If necessary apply a moisture sealer such as Soudal EPR-31P.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.