



# Soudaseal MS Clear

Revision: 17/02/2023 Page 1 from 3

#### **Technical data**

Basis	SMX Hybrid Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 4 min
Curing speed * (23°C/50% R.H.)	2 mm/24h → 3 mm/24h
Hardness**	38 ± 5 Shore A
Density	Ca. 1,05 g/ml
Elastic recovery (ISO 7389)**	> 75 %
Maximum allowed distortion	± 20 %
Max. tension (ISO 37)**	Ca. 1,80 N/mm²
Elasticity modulus 100% (ISO 37)**	Ca. 0,60 N/mm²
Elongation at break (ISO 37)**	Ca. 350 %
Temperature resistance**	-40 °C → 90 °C
Application temperature	$5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$

<sup>\*</sup> These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## **Product description**

Soudaseal MS Clear is a high quality, crystal clear, neutral, elastic, 1-component adhesive based on SMX-Polymer.

## **Properties**

- Crystal clear formulation
- Excellent adhesion on nearly all surfaces, even if slightly moist.
- · Very good mechanical characteristics.
- Impervious to mould, contains biocide with fungicidal action
- Suitable for sanitary applications.
- Good extrudability even at low temperatures
- Free of isocyanates, solvents, halogens and acids
- Can be painted with water based systems
- · Permanently elastic after curing

## **Applications**

- All common bonding applications, both in and outdoor.
- Sealing joints indoors.
- Transparent and elastic bonding in construction and building applications.

- Invisible bonding of glass and other transparent materials in indoor applications.
- Joints in bathrooms and kitchens.

## **Packaging**

Colour: transparent Packaging: 290 ml cartridge, other packaging on request

### Shelf life

15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

#### Chemical resistance

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

### **Substrates**

Substrates: all usual building substrates, glass, treated wood, PVC, plastics, metals, stone, concrete. ...

*Nature*: rigid, clean, dry or slightly moist, free of dust and grease.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





# Soudaseal MS Clear

Revision: 17/02/2023 Page 2 from 3

Surface preparation: Porous surfaces should be primed with Primer 150. Prepare nonporous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding or sealing. NOTICE: bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of Soudaseal MS Clear is not recommended in these applications. Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass. We recommend a preliminary adhesion and compatibility test on every surface.

## Joint dimensions

Min. width for bonding: 1 mm Min. width for joints: 5 mm Max. width for bonding: 3 mm Max. width for joints: 10 mm Min. depth for joints: 5 mm

## Application method

Application method: With a manual, pneumatic or accu caulking gun.

Cleaning: Clean with Soudal Surface Cleaner or with Soudal Swipex, immediately after use Cured Soudaseal MS Clear can only be removed mechanically.

Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material.

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

#### Remarks

- Soudaseal MS Clear is paintable with waterbased paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before appication.
- The drying time of alkyd resin based paints may increase.
- Soudaseal MS Clear can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from manufacturer to manufacturer, we recommend preliminary compatibilty test.
- Soudaseal MS Clear is not suitable for expansion joints.
- Do not use in applications where continuous water immersion is possible.
- Soudaseal MS Clear can discolour under extreme conditions or after very long UV exposure.
- Soudaseal MS Clear can not be used as a glazing sealant.
- Not suitable for bonding aquariums.
- Soudaseal MS Clear cannot be used on natural stone.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainigs will stimulate the development of fungi.
- A total absence of UV can cause a color change of the sealant.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





# Soudaseal MS Clear

Revision: 17/02/2023 Page 3 from 3

## **Environmental clauses**

Leed regulation:
Soudaseal MS Clear conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

## Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Everdongenlaan 18 - 20

Fax: +32 (0)14-42.65.14

Soudal NV Tel: +32 (0)14-42.42.31 B-2300 Turnhout, Belgium www.soudal.com