



Assembly Paste

Revision: 16/07/2019 Page 1 from 1

Technical data

Basis	Synthetic multipurpose EP-grease
Consistency	Stable paste
Viscosity	80 cSt at 40°C
Drop point	> 300°C
Temperature resistance**	-55 °C → 180 °C
Application temperature	5 °C → 30 °C

^{*} These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Assembly Paste is a specially developed professional assembly paste for moving parts such as bearings, headset and bottom bracket.

Properties

- Reduces friction in moving parts
- Facilitates assembly and disassembly.
- · Rust and corrosion-resistant
- Eliminates cracking and squeaking.
- Reduces friction and wear
- · Contains no heavy metals.
- Water-repellent

Applications

 Suitable for the assembly of moving parts such as bearings, headset and bottom bracket.

Packaging

Colour: light brown Packaging: 200 ml

Shelf life

2 years in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Nature: rigid, clean, dry, free of dust and grease.

Application method

Application method: Clean and degrease the parts in advance. Apply sufficient Assembly

Paste. Wipe away excess product with a cloth.

Health- and Safety RecommendationsTake the usual labour hygiene into account.

Remarks

 During application of Assembly Paste, avoid inclusion of dust and other impurities.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com