

## Protect and Polish

Revision: 16/07/2019

Page 1 from 1

### Technical data

Basis	Mixture based on silicone oil
Consistency	Liquid
Density	Ca. 0,74 g/ml
Acidity level (text)	Neutral
Solubility in water	Not soluble
Volatile Organic Compounds (VOC)	90 %
Temperature resistance**	-40 °C → 200 °C
Application temperature	5 °C → 30 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

### Product description

Protect and Polish is a transparent, professional polish to shine bicycle frames.

### Properties

- Glossy effect
- Temporary protection of the surface
- Water-repellent
- Reduces humidity
- Reduced dirt deposits
- Rust and corrosion-resistant
- Aerosol can be used in any angle (360°)

### Applications

- Forms a shiny thin film on the bicycle frame.
- Suitable for lacquered surfaces as well for aluminum and carbon.
- Forms a temporary protection and prevents dirt and grease deposits.
- Do not use on disc and rim brakes.
- Gives plastics and rubber a glossy finish.

### Packaging

*Colour:* transparent

*Packaging:* 400 ml aerosol

### Shelf life

3 years in unopened packaging in a dry and cool environment at temperatures between +5°C and +25°C.

### Substrates

*Nature:* clean, free of dust and grease.  
All types of metals and plastics.

### Application method

*Application method:* Surfaces must be cleaned, degreased and dry. Shake can well before use. Spray from a distance or apply with a clean cloth. Apply a thin layer evenly.

### Health- and Safety Recommendations

Use only in well-ventilated areas. In case of contact with eyes, wash immediately with plenty of water.

### Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.